

Afrisol Range of Cored Solder Wires

Metal Composition (% metal by weight)							
Designation	Flux Type	Sn	Pb	Cu	Ag	Availability	Sol/Liq Temp.
30S	Acid Core	30	70	-	-	-	183-255
40S	Acid Core	40	60	-	-	-	183-234
60S	Acid Core	60	40	-	-	-	183-189
40T2	Rosin Core	40	60	-	-	-	183-234
60T2	Rosin Core	60	40	-	-	-	183-189
63/37 SMT Plus	No Clean	63	37	-	-	-	183