

### Afrisol Range of White Metals

Metal Composition (% metal by weight)									
SABS Alloy No	Brinell Hardness	Sn	Sb	Cu	Ag	Bi	Cd	Pb	Pouring Temp.
<b>WM 90</b>	<b>26.5</b>	90.0	7.0	3.0	-	-	-	-	340-370
<b>WM 84</b>	<b>31.0</b>	84.0	10.0	6.0	-	-	-	-	410-460
<b>WM 80</b>	<b>30.5</b>	80.0	9.0	6.0	-	-	-	5.0	410-460
<b>WM 72</b>	<b>27.0</b>	72.0	10.0	6.0	-	-	-	12.0	410-450
<b>WM 40</b>	<b>24.2</b>	40.0	15.0	3.0	-	-	-	42.0	350-400
<b>WM 30</b>	<b>24.0</b>	30.0	16.0	1.0	-	-	-	53.0	350-400
<b>WM 15</b>	<b>24.0</b>	15.0	14.0	0.5	-	-	-	70.5	330-360
<b>WM 06</b>	<b>24.0</b>	6.0	14.0	-	-	-	-	80.0	320-340
<b>WM 11R</b>		90	7.5	3.0	-	-	-	-	
<b>WM 175</b>		75.0	14.5	7.5	-	-	-	3.0	